

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : B23K 26/12, G03F 7/42	A1	(11) International Publication Number: WO 98/10886 (43) International Publication Date: 19 March 1998 (19.03.98)
(21) International Application Number: PCT/IL97/00271 (22) International Filing Date: 11 August 1997 (11.08.97) (30) Priority Data: 119246 12 September 1996 (12.09.96) IL (71) Applicant (for all designated States except US): ORAMIR SEMICONDUCTOR EQUIPMENT LTD. [IL/IL]; P.O. Box 14, 31000 Haifa (IL). (72) Inventors; and (75) Inventors/Applicants (for US only): LIVSHITS, (BUYANER), Boris [IL/IL]; Yasmin Street 20/13, 21940 Carmiel (IL). GENUT, Menachem [IL/IL]; Leah Street 51, 34815 Haifa (IL). TEHAR-ZAHAV, Ofer [IL/IL]; Binyamin Avenue 28, 42311 Natania (IL). ISKEVITCH, Eliezer [IL/IL]; Anilevitch Street 1/11, Neve-Ganim, 26000 Kiryat-Mozkin (IL). (74) Agents: LUZZATTO, Kfir et al.; Luzzatto & Luzzatto, P.O. Box 5352, 84152 Beer-Sheva (IL).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	

(54) Title: LASER REMOVAL OF FOREIGN MATERIALS FROM SURFACES**(57) Abstract**

Method of fast and complete laser removal of inorganic and organic foreign material, including particles down to sub-micron sizes and atomic contaminants, such as heavy metals and alkaline elements, from a substrate without any damage to the substrate, carried out by UV laser irradiation of the substrate surface in a reactive oxygen based gas, which comprises carrying out the removal process in the presence of gas containing F and/or Cl atoms in its molecules.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LJ	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

LASER REMOVAL OF FOREIGN MATERIALS FROM SURFACES

Field of invention

The present invention relates to U.V. laser surface treatment methods, more particularly to removal of any foreign materials from substrate surfaces. For example, such a treatment is the complete stripping of photoresists or the removal of any foreign materials, including those on side walls, formed during Reactive Ion Etching (RIE) or High Dose Ion Implantation (HDI) processes, common in the VLSI/ULSI (Very/Ultra Large Scale Integration) circuits industry. The invention also includes the removal of particles down to sub-micron sizes and atomic contaminants, such as heavy metals and alkaline elements, from substrate surfaces.

Background of the invention

In the manufacturing of various products it is necessary to apply a layer of protective material on a surface, which must be removed after a specified manufacturing step has been concluded. An example of such process is the so-called "photolithography" process, which is widely used in the manufacturing of integrated circuits. In this process, a pattern is created on a surface using a layer of protective material illuminated through a mask, and the surface is then treated with a developer which removes material from the unmasked portions of the surface, therefore leaving a predetermined pattern. The surface is then treated by ion implantation or by etching agents, which introduce the implanted species into, or removes material from, the unmasked portions of the surface. Once these processes are completed, the role of the protecting mask ends and it must be removed. The process is conventional and well known in the art, and is described, e.g., in R.K. Watts, "Lithography", VLSI/ULSI Technology, S.M. Sze, ed., McGraw-Hill, New York, 1988, Chpt. 4.

Two main photoresist stripping methods are known in the modern VLSI/ULSI circuits industry (see D.L. Flamm, "Dry PlasmaResist Stripping", Parts 1, 2 and 3; Solid State Technology, August, September and October 1992):

- 1) Wet stripping which uses acids or organic solvents;
- 2) Dry stripping, which uses plasma, O_3 , O_3/N_2O or UV/ O_3 -based stripping.

Both methods are problematic and far from being complete, especially when taking into consideration the future miniaturization in the VLSI/ULSI industry. The current technology is capable of dealing with devices having feature sizes of about $0.5 \mu m$, but the workable size of the devices is expected to be reduced before the end of the century to $0.25 \mu m$. The expected size changes require considerable changes in the manufacturing technology, particularly in the stripping stage. The prior art photoresist stripping techniques, described above, will be unsuitable for future devices, as explained hereinafter.

Utilizing only the wet stripping method is not a perfect solution, as it cannot completely strip photoresist after tough processes that change the chemical and physical properties of the photoresist in a way that it makes its removal very difficult. Such processes include, e.g., High Dose Implantation (HDI), reactive Ion Etching (RIE), deep UV curing and high temperatures post-bake. After HDI or RIE, the side walls of the implanted patterns or of the etched walls are the most difficult to remove.

In addition, the wet method has some other problems: the strength of stripping solutions changes with time, the accumulated contamination in solutions can be a source of particles which adversely affect the performance of the wafer, the corrosive and toxic content of stripping chemicals imposes

high handling and disposal costs, and liquid phase surface tension and mass transport tend to make photoresist removal uneven and difficult.

The dry method also suffers from some major drawbacks, especially from metallic and particulate contamination, damage due to plasma: charges, currents, electric fields and plasma-induced UV radiation, as well as temperature-induced damage, and, last but not least, it suffers from incomplete removal. During various fabrication stages, as discussed above, the photoresist undergoes chemical and physical changes which harden it, and this makes the stripping processes of the prior art extremely difficult to carry out. Usually a plurality of sequential steps, involving wet and dry processes are needed to remove completely the photoresist.

The art has addressed this problem in many ways, and commercial photoresist dry removal apparatus is available, which uses different technologies. For instance, UV ozone ashers are sold, e.g. by Hitachi, Japan (UA-3150A). Dry chemical ashers are also available, e.g., by Fusion Semiconductor Systems, U.S.A., which utilize nitrous oxide and ozone to remove the photoresist by chemical ashing at elevated temperatures. Microwave plasma ashing is also effected, e.g., as in the UNA-200 Asher (ULVAC Japan Ltd.). Also plasma photoresist removal is employed and is commercially available, e.g., as in the Aspen apparatus (Mattson Technology, U.S.A.), and in the AURA 200 (GASONICS IPC, U.S.A.).

More recently, photoresist removal has been achieved by ablation, using laser UV radiation, in an oxidizing environment, as described in U.S. Patent No. 5,114,834. The ablation is due to strong absorption of the laser pulse energy by the photoresist. This process is a localized ejection of the photoresist layer to the ambient gas, associated with a blast wave due to the breaking of chemical bonds in the photoresist and instant heating. The partly gasified and partly fragmented photoresist is blown upwards away

from the surface, and instantly heats the ambient gas. Fast combustion of the ablation products occurs due to the blast wave, and may also be due to the photochemical reaction of the UV laser radiation and the process gases. The main essence of the process is laser ablation with combustion of the ablated photoresist, which occurs in a reactive gas flowing through an irradiation zone. The combination of laser radiation and fast combustion provides simultaneous lowering of the ablation threshold of hard parts of the photoresist (side walls). The combusted ablation products are then removed by vacuum suction, or by gas sweeping leaving a completely clean surface.

While US 5,114,834 provides an important novel process, it still does not provide a high throughput, which is industrially convenient, viz., an industrially acceptable number of wafers that can be stripped during a given time. The laser stripping throughput is determined by the stripping rate or by the number of laser pulses needed for providing complete stripping of a unit area of the photoresist per unit of time.

International Patent Application No. PCT/IL96/00138, published under the number WO 97/17166, the entire content of which is incorporated herein by reference, discloses a method of accelerating a laser stripping process carried out in a reactive gas mixture, comprising carrying out the stripping process in the presence of an accelerating effective amount of N_xO_y gas, preferably selected from among N_2O , NO , NO_2 , N_2O_3 , N_2O_4 and NO_3 . The reactive gas mixture may include oxygen or ozone. While oxygen based chemistry provides a good solution for assisting laser removal of organic materials, it does not give a complete answer for removing inorganic based residues with ablation threshold which exceeds the damage threshold of the substrate. Such residues are formed, for example, on side walls during RIE processes as in etching of metal, polysilicon, contacts, and via holes. The

oxygen based gas composition described in WO 97/17166 gives atomic oxygen radicals. These radicals cannot break the strong chemical bonds in inorganic materials, as e.g. Si-O, Si-C, Si-Cl or other metal-oxygen bonds. Therefore the removal of the above mentioned residues containing such bonds is one of the challenges in dry stripping. Another challenge is the removal of submicron particles, as well as metallic contaminants, from silicon wafers or from other substrates. This is extremely important for ULSI technology.

While reference will be made throughout this specification to laser removal of foreign materials from semiconductor wafers, this will be done for the sake of simplicity, and because it represents a well known and widely approached problem. It should be understood, however, that the invention described hereinafter is by no means limited to laser removal of foreign materials from wafers, but it applies, *mutatis mutandis*, to many other applications, such as cleaning of foreign materials from different objects such as Flat Panel Displays (FPD), lenses, photo-masks, compact disks, magnetic heads etc.

Summary of the invention

It has now surprisingly been found, that addition of gases, the molecules of which contain fluorine and/or chlorine atoms, to the oxygen-based process gases used for laser removal of foreign materials, including particles and atomic contaminants, such as heavy metals, alkaline elements and atomic elements, in the method described in the aforementioned International Publication No. WO 97/17166 - which gases contain at least a gas having the formula N_xO_y , viz. one or more nitrogen oxides, wherein x and y having the appropriate values for the given oxide or mixtures of the oxides, preferably selected from among N_2O , NO, NO_2 , N_2O_3 , N_2O_4 and NO_3 , permits the fast and complete removal of inorganic in addition to the

organic foreign materials, for example removal of adhesion promoters and/or antireflection coatings used prior to photoresist application. This effect was also proved even for submicron geometries common in modern and future ULSI industry.

Accordingly, the method of accelerating a Laser Removal Process (LRP) carried out in reactive gas mixture, according to the invention, comprises carrying out the stripping process in the presence of an oxygen based gas $O_2/O_3/N_xO_y$ and of a gas containing fluorine and/or chlorine in its molecule.

At elevated values of laser energy fluence and/or auxiliary gas irradiation by VUV source (vacuum UV, wavelength lower than 180 nm) one can choose a gas containing F and/or Cl atoms in its molecule from among NF_3 , SF_6 , SF_4 , CF_4 , CF_3 , $NOCl$, Cl_2O , F_2O , HF , F_2 , Cl_2 , HCl .

The most preferred gas containing fluorine and/or chlorine atoms in its molecule is nitrogen trifluoride (NF_3), due to its lower thermo-dissociation energy. This gas promotes fast and complete laser removal of inorganic foreign materials, including micron and submicron particles and metallic contaminants, as well as preventing any damage to the treated substrates.

Brief Description of the Drawings

In the drawings:

Fig. 1 is a plan view, from the bottom, of a process chamber as described and claimed in the aforementioned International Patent Application of the same applicant, which is preferably used in carrying out the present invention;

Fig. 2 is cross-section of the same, taken along plane II-II of Fig. 1; and

Figs. 3 and 4 are details illustrating, in the same cross-section, different positions of the wafer to be treated.

Detailed description of Preferred Embodiments

The method of laser removal of foreign materials, according to this invention, comprises adding an amount of a gas containing chlorine and/or fluorine in its molecule, preferably nitrogen trifluoride (NF_3), to the reactive gas mixture applied in laser stripping, as described in the aforementioned International Publication No. WO 97/17166, whereby to achieve fast and complete removal of the foreign inorganic as well as metalorganic and silicon-organic materials (film, particles down to sub-micron sizes and atomic contaminants) from a wafer.

Decomposition of halogen containing molecules is feasible by photolysis in UV, by plasma electrons and also by thermo-dissociation. In the LPR method, thermo-dissociation is the common way for obtaining primary fluorine or chlorine atoms from appropriate molecules in the process gas irradiated by excimer laser. NF_3 is chosen because of its lower $\text{NF}_x\text{-F}$ bond energies in comparison with other fluorine containing molecules, which promotes easier thermo-dissociation. NF_3 dissociates effectively already at $\sim 450^\circ\text{C}$. Since the temperature of the Laser Induced-Gas Medium is higher than 450°C , considerable thermo-dissociation of NF_3 will occur.

An additional amount of F atoms is induced by chemical reactions of atomic oxygen with radicals NF_2 and NF which are formed as a result of NF_3 thermo-dissociation.

The energy fluences used for laser removal of foreign materials are much lower than is required for etching the substrate, being significant for more effective etching of residues and particles. It promotes the following chemical etching by atomic fluorine and facilitates the consequent laser etching of all foreign material. Thus this chemical assisted laser etching (as

one of mechanisms of laser removal of foreign materials) determines its selectivity.

An important requirement for any chlorine and/or fluorine containing gas, to be used according to the invention, is its low spontaneous reactivity with the substrate. NF_3 satisfies this requirement. One should also emphasize that, as opposed to the plasma stripping method, the process gas in LRP remains without atomic radicals during most of the exposure time. This should also favor the selectivity of the LRP method.

Application of NF_3 allows to minimize the degradation of silicon oxide during the LRP, which is especially important for submicron geometry, by lowering the wafer's temperature. For that it is needed to expand a process window by appropriate pulse extension in accordance with the disclosure of International Patent Application No. PCT/IL96/00139, published under the number WO 97/17164. It will provide a damage free surface treatment at elevated fluence values with lower substrate temperature. This latter should decrease the interaction of F atoms with silicon oxide and silicon.

On the other side, the elevated values of fluence should lower the effective concentrations of NF_3 and may permit the use of other fluorine containing additives, such as SF_6 , SF_4 , CF_3Cl , NOCl , Cl_2O , F_2O , HF , F_2 , Cl_2 , HCl , CF_4 as well as a number of other molecules containing F and/or Cl.

In addition, a supplementary generation of halogen atoms by photodissociation could be implemented by means of an auxiliary source of VUV-radiation ($\lambda < 180 \text{ nm}$).

One specific embodiment of the invention is the removal of micron and sub-micron particles from substrates, in particular silicon wafer. The removal is

effected by laser induced chemical etching followed by laser etching. This process is highly selective.

Example 1 (comparative)

A 6" wafer after poly-silicon deposition was covered with a layer of Novolak type positive photoresist, 1.2 μm thick, patterned by the conventional procedure mentioned hereinbefore, with features size down to 0.35 μm , and then was subjected to RIE of polysilicon pattern. During the RIE process, the poly-silicon sidewalls, as well as the photoresist, were covered with an silicon-organic polymeric film forming on the so-called sidewalls.

Following the RIE, the wafer was treated in a process chamber. One should understand that the process chamber hereinafter described is only a particular example. Many types of process chambers can be used for the processes described in this specification and the description of a particular chamber does not constitute a limitation or a suggestion that the specific configuration of such a chamber is necessary or required. It should be emphasized that this invention is not limited to any particular shape or size of process chamber, and can be carried out in performing laser treatments on much larger or much smaller surfaces and in process chambers of different shapes and made of different materials.

The process chamber herein exemplified consists of a base and a cover, which are connected by air-tight connections so that the inner part of the process chamber defined by the said base and cover can be kept under pressure or vacuum. The base is provided with N_2O_y gas inlet, and O_2/O_3 inlet, and gas outlet for exhausting gases which have passed through the irradiated zone. The base is further provided with a chuck, on which the element to be stripped, e.g., a wafer, is supported. Through the center of chuck, vacuum is applied, to hold the wafer in place during the process. A fused silica window is provided above the element to be stripped, e.g., a

silicon wafer. This window permits the passage of the laser beam, which originates from a source positioned above the chamber. A silica cover frame keeps the silica windows in place, and assists in keeping the chamber pressurized or under vacuum.

Such a chamber is described and claimed in an International Patent Application No. PCT/IL96/00141, published under the number WO 97/17167, the description of which is incorporated herein by reference, and which is briefly described hereinafter, for purposes of illustration, with reference to the drawings.

The process chamber, shown in plan view from the bottom in Fig. 2 and in vertical cross-section in Fig. 2, comprises a base 2, and a cover 3, which are connected by air-tight connections (not shown), so that the inner part of the process chamber, defined by the said base 2 and cover 3, can be kept under pressure or vacuum. The base 2 is provided with N_xO_y gas inlet 4, and O_2/O_3 inlet, and gas outlet 5, for exhausting gases which have passed through the irradiated zone. The base 2 is further provided with a chuck 6, on which the element to be stripped, e.g., a wafer, is supported. Through the center of chuck 6 vacuum is applied, to hold the wafer in place during the process.

Two seals, 11A and 11B are shown in Fig. 2, which may be, e.g., O-rings. These two seals define two vacuum zones in the process chamber:

a) Zone 1, which defines the ablation environment in the irradiation zone. The pressure is maintained by means of throttle valve connected in a closed loop to a pressure controller. Typical pressure is in the range of 50 - 2000 mbar. this pressure regime is defined by seal 11B.

b) Zone 2, which defines the pressure in the outside vacuum channel 20 in between seals 11A and 11B.

The pressure in the channel is always much lower than in the process chamber and usually is in the order of a few millibars or typical vacuum obtainable from mechanical vacuum pumps. The outer vacuum channel 20 has two main purposes: to maintain firmly cover 3 through the aid of the atmospheric pressure, and to permit, in case of a leak, the leaking gas to be sucked by the vacuum pump connected to channel 20.

The wafer is positioned above chuck 6 and below window 9, as indicated by numeral 12. Wafer 12 can be positioned on chuck 6 in two ways, as shown in Figs. 3 and 4. In Fig. 3 the wafer is on top of chuck 6. In Fig. 4 the wafer is immersed inside chuck 6. The wafer does not touch window 9, and there is a distance between them which is preferably kept in the range of 0.2 - 10 mm. This distance can be varied as long as the product of the values of $P \times h$ remains approximately constant, wherein P is the pressure above the wafer and h is the gap, as hereinbefore defined. The pressure referred to above is measured in the center of the process chamber in the irradiation zone.

The space between the window and the wafer defines the ablation cassette cell, through which the gases flow, and in which the ablation products are jetted from the wafer, ignited and combusted. Looking at gas inlet stagnation cell 7, it can be seen that the inflowing gases flow into the ablation cell through a communication opening indicated by numeral 13.

The window above the wafer is preferably made of fused silica, to fulfill certain requirements such as optical quality, to permit maximum passage of

the incident laser beam (indicated in the figure by the LB arrow), durability, resistance to process gases and temperature, mechanical strength, etc.

The process was operated according to U.S. Patent No. 5,114,835 and to the aforementioned International publication no. WO 97/17166, using ozone and N_xO_y as the reactive gas. The laser employed was a Lambda Physik LPX315 IMC excimer laser. During the stripping process, the wafer was maintained at 150-250°C by the chuck, which was externally heated by an electrical resistive heater.

The total pressure in the process chamber was slightly below atmospheric pressure, and the N_xO_y volumetric concentration was varied between 5 and 30%.

Different spots on the wafer were irradiated by different numbers of pulses, and then the wafer was examined by High Resolution Scanning Electron Microscopy (SEM). Complete stripping without residues was not found even after 1500 pulses, which is not a reasonable number of pulses to be used in an industrial process. Even after 1500 pulses, a significant amount of residue in the form of sidewalls could be observed.

Example 2 (comparative)

The same operations as in Example 1 were carried out, but with the introduction of chlorine gas into the gas mixture. Different concentrations of Cl_2 were tried and the best conditions were found with 15 mbar Cl_2 partial pressure. As in Example 1, 1500 pulses were used.

After examination by the SEM, it was found that the process was improved compared to Example 1; however, some sidewalls residue still remained.

Example 3 (comparative)

The same operations as in Example 1 were carried out, but with the introduction of fluorine gas into the gas mixture. The F_2 was introduced by mixing it with the O_2/O_3 gas. Different concentrations of F_2 were tried and the best conditions were found with 0.3 mbar partial pressure of F_2 . As in Example 1, 1500 pulses were used.

After examination by the SEM, it was found that the process was much improved compared to Example 1; however, some few sidewall residues still remained. In addition, evidence of chemical damage of the substrate was also observed by the SEM. This shows the bad selectivity of F_2 .

Example 4

The same operations as in Example 1 were carried out, but with the introduction of NF_3 gas into the gas mixture. Different concentrations of NF_3 were tried and the best conditions were found with ~800 mbar partial pressure of NF_3 .

After examination by the SEM, it was found that a complete process without any sidewall residue was found, even when the total number of pulses was below 500. This is an improvement of the throughput by more than three times in comparison with the previous examples, in which 1500 pulses were applied.

Example 5

A wafer after via hole RIE was stripped as in Example 4. Complete removal of photoresist and sidewalls was verified by SEM.

Example 6

The operations of Example 6 were repeated, but with a wafer after contact hole RIE.

Example 7

A 6" Bare Silicon wafer was measured with a particle detector (Tencor 4000 Surfscan) and the number of particulates greater than 0.3 μm was recorded.

Following the measurement, the wafer was treated in a process chamber as described in Example 1. The process was operated according to U.S. Patent No. 5,114,835 and aforementioned International Publication No. WO 97/17166, using ozone and N_2O_y as the reactive gas, as described in Example 1.

During the process, the wafer was maintained at room temperature.

After the entire wafer was processed, it was tested by the Surfscan and it was found that the number of particles was reduced by approximately 40%.

Example 8

The operations of Example 7 were repeated, but the wafer was maintained at 150-250°C. In this case, it was found that about 50% of the particles were removed.

Example 9

The operations of Example 8 were repeated, but in addition to the O_3 and N_2O_y , NF_3 was added to the gas mixture as described in Example 4.

In this case, it was found that about 70% of the particles were removed during the process. The wafer was maintained at room temperature.

Example 10

The operations of Example 9 were repeated, but the wafer was maintained at 150-250°C. In this case, about 90% of the particles were removed.

Example 11

The operations of Example 10 were repeated, but the wafer was subjected to 3-5 passes through the process chamber. In this case, almost all of the particles were removed.

Example 12

A 6" wafer, covered with photoresist as in Example 1, was stripped according to the process described in Example 1. After stripping the wafer was checked by Vapor Phase Decomposition Total Reflection X-Ray Fluorescence (VPD-TXRF) and the surface concentration of heavy metals such as Ti, Cr, Fe and Ni was found to be in the range of 10^{11} - 10^{12} atoms/cm².

Example 13

The operations of Example 12 were repeated, but NF₃, up to 400 mbars, was added to the gas mixture. After stripping the surface, heavy metal concentrations were found to be reduced up to one order of magnitude.

While specific embodiments of the invention have been described for the purpose of illustration, it will be understood that the invention may be carried into practice by skilled persons with many modifications, variations and adaptations, without departing from its spirit or exceeding the scope of the claims.

CLAIMS

1. Method of fast and complete laser removal of inorganic and organic foreign material, including particles down to sub-micron sizes and atomic contaminants, such as heavy metals and alkaline elements, from a substrate without any damage to the substrate, carried out by UV laser irradiation of the substrate surface in a reactive oxygen based gas, which comprises carrying out the removal process in the presence of gas containing F and/or Cl atoms in its molecules.
2. Method according to claim 1, wherein the reactive gas mixture contains oxygen or ozone.
3. Method according to claims 1 and 2, wherein the reactive oxygen-based gas contains nitrogen oxide (N_xO_y).
4. Method according to claim 1, wherein the irradiation is produced by excimer laser.
5. Method according to claims 1 and 4, which comprises additional irradiation by excimer lamp or other VUV sources.
6. Method according to claim 1 or claim 5, wherein the gas containing fluorine and/or chlorine in its molecule is chosen from among NF_3 , SF_6 , SF_4 , CF_4 , $NOCl$, CF_3Cl , HF , Cl_2 , Cl_2O , F_2O , HCl and other molecules containing F and/or Cl.
7. Method according to claim 1 or claim 5, wherein the gas containing fluorine and/or chlorine in its molecule is a gas which produces fluorine and/or chlorine atoms by thermo-dissociation when irradiated by UV laser.

8. Method according to claim 1 or claim 5, wherein the gas containing fluorine and/or chlorine in its molecule is present in an amount up to 95% by volume of the reactive gas mixture.
9. Method according to claim 1, wherein the gas containing fluorine is NF_3 .
10. Method according to claim 1, for the removal of thin films.
11. Method according to claims 1 and 10, for the removal of photoresist .
12. Method according to claim 1, for the removal of micron and submicron particles.
13. Method according to claims 11 and 12, wherein the substrate is a silicon wafer.
14. Method according to claims 11 and 12, wherein the substrate is a Flat Panel Display.
15. Method according to claims 11 and 12, wherein the substrate is a compact disc.
16. Method according to claims 11 and 12, wherein the substrate is a magnetic head.
17. Method of laser removal of foreign materials, including particles down to sub-micron sizes and atomic contaminants, such as heavy metals and alkaline elements, from a substrate without any damage to the substrate, substantially as described.

1/2




Fig. 1




Fig. 2




Fig. 3

Fig. 4

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/IL 97/00271

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B23K26/12 G03F7/42

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B23K G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 97 17166 A (ORAMIR SEMICONDUCTOR LTD ;LIVSHITS BUYANER BORIS (IL); GENUT MENAC) 15 May 1997 cited in the application see page 5, paragraph 1 see page 6, paragraph 2 see page 7, last paragraph ---	1-17
X	US 5 114 834 A (NACHSHON YEHUDA) 19 May 1992 cited in the application see column 3, line 52 - line 55 see column 5, line 58 - line 63 -----	1-17

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"B" document member of the same patent family

Date of the actual completion of the international search

21 November 1997

Date of mailing of the international search report

10.12.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pricolo, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IL 97/00271

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9717166 A	15-05-97	AU 7330996 A	29-05-97
US 5114834 A	19-05-92	DE 3835636 A	03-05-89
		FR 2622352 A	28-04-89
		FR 2622134 A	28-04-89
		GB 2211629 A,B	05-07-89
		NL 8802587 A	16-05-89